PikoFlon



Cover Type:	Carbide	
Hardness Range:	1100 Vickers	
Available Colours:	black	
Recommended Cover Thickness:	Standard 150 µm	max. 1000 μm
Temperature resistance:	Dry:	continuous 150°C / peak 210°C
Specific characteristics:	Bonding strength: Surface roughness (Ra):	> 75 MPa min. 2 μm - max. 4 μm
Chemical resistance:	Acid solutions: Alkaline solutions: Hot water and steam: Ozone: Oil and grease: Chlorinated solvents: Polar solvents (MEC, ether, acetate,)	Good Good Good Good Very good Not suited :
Remark:	- reference list available on demand - good resistance to standard chemicals normally used in paper machines	

