MultiCoat-SB-AS

Print date: 11/05/2024



| Cover Type: | Rubber | |
|--------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------|
| Possible applications: | Metals and metal packaging industry: applicator rollers and wheels for primer coating, lacquering, varnishing and chemical coating Wood and wood laminate: varnishing rollers, glue applicators Conversion of paper and film – adhesive and release stock: primer, glue and silicone applicator rollers and sleeves | |
| | | |
| | | |
| | Hardness Range: | 35, 50, 55, 60, 65, 70, 75 Shore A |
| Available Colours: | black | |
| Temperature resistance: | Dry: Wet: | continuous 110°C / peak 125°C continuous 80°C / peak 90°C |
| Properties and advantages: | Good physical properties | |
| | Excellent resistance to polar solvents (MEC, acetates, alcohols) | |
| | Very good surface wetting and transfer properties | |
| | High purity and homogeneity | |
| | Easy to grind and to groove | |
| | Antistatic | |
| Specific characteristics: | Antistatic | |
| Chemical resistance: | Acid solutions: Alkaline solutions: Hot water and steam: Ozone: Oil and grease: Aromatic solvents (toluene, benzene,): Chlorinated solvents: Polar solvents (MEC, ether, acetate,): | Very good Very good Very good Excellent Not suited Not suited Not suited Excellent |
| Recommended cleaning products: | (Warm) water, soap, detergent, acid/alkaline cleaners, polar solvents : MEK, alcohol, acetate | |

