Resistoplast

Print date: 11/05/2024



Cover Type:	Special rubber	
Possible applications:	Tissue paper converting : embossing rollers	
	Embossing rollers in other industrial areas : PVC, wall paper, plastic film, flexible packaging, non-woven, wood and décor Textile and non-woven converting : calendering and laminator rollers	
Hardness Range:	45, 50, 55, 60, 65, 70, 75, 80, 85, 90 Shore A 72, 90 Shore D	
Available Colours:	green, grey	
Recommended Cover Thickness:	min. 10 mm - max. 20 mm	
Temperature resistance:	Dry:	continuous 125°C / peak 140°C
Properties and advantages:	High resistance to mechanical stress High resilience (fast elastic recovery to the original shape) Superior abrasion resistance Consistent hardness in time Suitable for point-to-point, nested and random embossing technologies Suitable for high machine speed (up to 800 m/min) Faithful and constant pattern reproduction	
Chemical resistance:	Acid solutions: Alkaline solutions: Hot water and steam: Ozone: Oil and grease: Aromatic solvents (toluene, benzene,): Chlorinated solvents: Polar solvents (MEC, ether, acetate,): Alcohols (ethanol, IPA,): Ageing resistance:	Very good Good Good Very good Good Not suited Not suited Not suited Very good Very good
Recommended cleaning products:	(Warm) water, soap, industrial cleaners and detergents, alcohol, (diluted) acid cleaners	
Remark:	Resistoplast-D and Resistoplast-T : multilayer solutions for optimized results in specific, demanding applications	

