


# Hannethane-SM



<b>Cover Type:</b>	Polyurethane	
<b>Possible applications:</b>	Production of metal strip : looper, strip support and conveyor rollers, bridle, steering and deflector rolls, pinch rolls, rollers for oiling, deflector rolls in some chemical environments	
<b>Hardness Range:</b>	70, 80, 90, 95 Shore A	
<b>Recommended Cover Thickness:</b>	min. 7 mm - max. 20 mm	
<b>Temperature resistance:</b>	Dry:	continuous 90°C / peak 100°C
	Wet:	continuous 50°C / peak 70°C
<b>Properties and advantages:</b>	Excellent abrasion resistance Very good resistance to tear and cutting Very high elasticity	
<b>Chemical resistance:</b>	Acid solutions:	Moderate
	Alkaline solutions:	Moderate
	Hot water and steam:	Not suited
	Ozone:	Very good
	Oil and grease:	Excellent
	Aromatic solvents (toluene, benzene,...):	Not suited
	Chlorinated solvents:	Not suited
	Polar solvents (MEC, ether, acetate,...):	Not suited
	Alcohols (ethanol, IPA,...):	Good
<b>Recommended cleaning products:</b>	(Tepid) water, soap, industrial cleaners, cleaning fuel, terpentine, with limited use : alcohol	