

Hannethane-AS



Cover Type:	Polyurethane	
Possible applications:	<p>All industries : rollers & wheels where very high mechanical properties & abrasion resistance are required, in combination with antistatic properties</p> <p>Plastic film production & converting, adhesives, non-woven, aluminium foil : conveyor, detour, tensioning & nip rollers - laminator rollers</p> <p>Web winding & cutting : idler, conveyor, contact & nip rollers</p> <p>Separator rollers for aluminium foil</p>	
Hardness Range:	40, 50, 60, 70, 75, 80, 90 Shore A	
Recommended Cover Thickness:	min. 10 mm - max. 25 mm	
Temperature resistance:	Dry: Wet:	continuous 80°C / peak 90°C continuous 50°C / peak 60°C
Properties and advantages:	<p>Excellent mechanical properties</p> <p>Excellent abrasion, tear and cut-in resistance</p> <p>Very good deformation recovery, high resilience</p> <p>Improved release properties towards plastic film</p>	
Specific characteristics:	Antistatic	
Chemical resistance:	Acid solutions: Alkaline solutions: Hot water and steam: Ozone: Oil and grease: Aromatic solvents (toluene, benzene,...): Chlorinated solvents: Polar solvents (MEC, ether, acetate,...): Alcohols (ethanol, IPA,...):	Moderate Good Not suited Good Very good Moderate Not suited Not suited Good
Recommended cleaning products:	(Tepid) water, soap, industrial cleaners, cleaning fuel, terpentine, alcohol with limited use	