



<b>Cover Type:</b>	Polyurethane	
<b>Possible applications:</b>	<p>Production of metal strip : squeegee and sink rolls in (hot) water and alkaline environment : water rinse, water quench, cleaning/degreasing - squeegee rolls for passivation and phosphatation</p> <p>Hold-down rolls on electrotrolytical plating lines (pre-treatment, plating and post-treatment sections)</p>	
<b>Hardness Range:</b>	75, 85 Shore A	
<b>Recommended Cover Thickness:</b>	min. 15 mm - max. 20 mm	
<b>Temperature resistance:</b>	Dry:	continuous 90°C / peak 100°C
	Wet:	continuous 70°C / peak 85°C
<b>Properties and advantages:</b>	<p>PU-Range with improved resistance to hydrolytic environments - suited for hot (demineralized) water and alkaline solutions - in some cases suited for diluted acid solutions</p> <p>Very high abrasion, tear and cut-in resistance</p> <p>High resilience, good squeezing behaviour - high energy efficiency</p>	
<b>Chemical resistance:</b>	Acid solutions:	Moderate
	Alkaline solutions:	Good
	Hot water and steam:	Good
	Ozone:	Good
	Oil and grease:	Very good
	Aromatic solvents (toluene, benzene,...):	Moderate
	Chlorinated solvents:	Not suited
	Polar solvents (MEC, ether, acetate,...):	Not suited
	Alcohols (ethanol, IPA,...):	Good
<b>Recommended cleaning products:</b>	(Tepid) water, soap, industrial cleaners, cleaning fuel, terpentine, with limited use : alcohol	
<b>Remark:</b>	In case of temperatures higher than 60 °C in wet applications, it is strongly recommended to use the special Hannecard PRINTAM® base layer in order to avoid chemical attack of the bonding between PU and core	