


# Hannethane-S



<b>Cover Type:</b>	Polyurethane	
<b>Possible applications:</b>	Production of metal strip : looper, strip support and conveyor rollers, bridle and detour rolls, pinch rolls  All industries : conveyor, support and back-up rollers - generally rollers submitted to high abrasion  Applications related to the textile, glass, wood, paper and board industry and to the production of packaging and plastic film	
<b>Hardness Range:</b>	60, 70, 80, 90, 95 Shore A	
<b>Recommended Cover Thickness:</b>	min. 7 mm - max. 20 mm	
<b>Temperature resistance:</b>	Dry: Wet:	continuous 90°C / peak 100°C continuous 50°C / peak 60°C
<b>Properties and advantages:</b>	Excellent abrasion resistance Very good resistance to tear and cutting Very high elasticity Not recommended for wet environments above 60 °C	
<b>Chemical resistance:</b>	Acid solutions: Alkaline solutions: Hot water and steam: Ozone: Oil and grease: Aromatic solvents (toluene, benzene,...): Chlorinated solvents: Polar solvents (MEC, ether, acetate,...): Alcohols (ethanol, IPA,...):	Moderate Moderate Not suited Very good Excellent Not suited Not suited Not suited Good
<b>Recommended cleaning products:</b>	(Tepid) water, soap, industrial cleaners, cleaning fuel, terpentine, with limited use : alcohol	