

# HanneStar-AS



<b>Cover Type:</b>	Rubber
<b>Possible applications:</b>	<p>Diverse applications in a lot of industrial areas : textile, packaging, (card)board, plastic film, converting, glass, wood etc., requiring good physical and antistatic properties</p> <p>Plastic film production &amp; conversion, flexible packaging - winding &amp; slitting : nip, conveyor and lay-ojn rollers, spreader rollers, stripping rollers</p> <p>Rollers and wheels in contact with oil, fuel or grease, needing antistatic properties or in ATEX environment</p>
<b>Hardness Range:</b>	45, 50, 60, 65, 70, 80 Shore A
<b>Available Colours:</b>	black
<b>Recommended Cover Thickness:</b>	min. 10 mm - max. 25 mm
<b>Temperature resistance:</b>	Dry: continuous 90°C / peak 110°C Wet: continuous 60°C / peak 80°C
<b>Properties and advantages:</b>	<p>Excellent resistance to mineral and vegetal oil, fuel, grease and (animal) fat</p> <p>Very good physical properties, tear and abrasion resistance, good elasticity and resilience</p> <p>Antistatic</p>
<b>Specific characteristics:</b>	Antistatic
<b>Chemical resistance:</b>	Acid solutions: Good Alkaline solutions: Very good Hot water and steam: Good Ozone: Good Oil and grease: Excellent Aromatic solvents (toluene, benzene,...): Moderate Chlorinated solvents: Not suited Polar solvents (MEC, ether, acetate,...): Not suited Alcohols (ethanol, IPA,...): Very good
<b>Recommended cleaning products:</b>	(Hot) water, soap, most industrial cleaners, alcohol, light fuel, turpentine, white spirit