HanneStar-AS

Print date: 03/05/2025



Cover Type:	Rubber		
Possible applications:	Diverse applications in a lot of industrial areas: textile, packaging, (card)board, plastic film, converting, glass, wood etc., requiring good physical and antistatic properties Plastic film production & conversion, flexible packaging - winding & slitting: nip, conveyor and lay-ojn rollers, spreader rollers, stripping rollers		
	Rollers and wheels in contact with oil, fuel or grease, needing antistatic properties or in ATEX environment		
Hardness Range:	45, 50, 60, 65, 70, 80 Shore A		
Available Colours:	black		
Recommended Cover Thickness:	min. 6 mm - max. 25 mm		
Temperature resistance:		continuous 90°C / peak 110°C continuous 60°C / peak 80°C	
Properties and advantages:	Excellent resistance to mineral and vegetal oil, fuel, grease and (animal) fat		
	Very good physical properties, tear and abrasion resistance, good elasticity and resilience		
	Antistatic		
Specific characteristics:	Antistatic		
Chemical resistance:	Acid solutions: Alkaline solutions: Hot water and steam: Ozone: Oil and grease: Aromatic solvents (toluene, benzene,): Chlorinated solvents: Polar solvents (MEC, ether, acetate,): Alcohols (ethanol, IPA,):	Good Very good Good Good Excellent Moderate Not suited Not suited Very good	
Recommended cleaning products:	(Hot) water, soap, most industrial cleaners, alcohol, light fuel, terpentine, white spirit		

