

HanneStar-AS



Cover Type:	Rubber
Possible applications:	Diverse applications in a lot of industrial areas : textile, packaging, (card)board, plastic film, converting, glass, wood etc., requiring good physical and antistatic properties Plastic film production and conversion, flexible packaging - winding & slitting : nip, conveyor and lay-ojn rollers, spreader rollers Rollers and wheels in contact with oil, fuel or grease, needing antistatic properties or in ATEX environment
Hardness Range:	45, 50, 60, 65, 70, 80 Shore A
Recommended Cover Thickness:	min. 10 mm - max. 25 mm
Temperature resistance:	Dry: continuous 90°C / peak 110°C Wet: continuous 60°C / peak 80°C
Properties and advantages:	Excellent resistance to mineral and vegetal oil, fuel, grease and (animal) fat Very good physical properties, tear and abrasion resistance, good elasticity and resilience Antistatic
Specific characteristics:	Antistatic
Chemical resistance:	Acid solutions: Good Alkaline solutions: Very good Hot water and steam: Good Ozone: Good Oil and grease: Excellent Aromatic solvents (toluene, benzene,...): Moderate Chlorinated solvents: Not suited Polar solvents (MEC, ether, acetate,...): Not suited Alcohols (ethanol, IPA,...): Very good
Recommended cleaning products:	(Hot) water, soap, most industrial cleaners, alcohol, light fuel, terpentine, white spirit