

WoodBond-S



Cover Type:	Rubber
Possible applications:	Production of wood, wood board and wood laminate : - applicator and transfer rollers for cold glue, water or formaldehyde based - applicator rollers for hardeners and catalysts
Hardness Range:	40, 45, 50, 65, 70, 80, 95 Shore A
Recommended Cover Thickness:	min. 10 mm - max. 20 mm
Temperature resistance:	Dry: continuous 100°C / peak 110°C Wet: continuous 60°C / peak 70°C
Properties and advantages:	Very good surface wetting and transfer properties Good physical properties and lifetime High purity and homogeneity Excellent oil resistance Easy to grind and to groove
Specific characteristics:	Semi-conductor
Doctoring:	TEST
Internal cooling:	TEST
Max. linear load:	fTEST
Chemical resistance:	Acid solutions: Moderate Alkaline solutions: Good Hot water and steam: Moderate Ozone: Very good Oil and grease: Wyjątkowy Aromatic solvents (toluene, benzene,...): Moderate Chlorinated solvents: Not suited Polar solvents (MEC, ether, acetate,...): Not suited Alcohols (ethanol, IPA,...): Very good Ageing resistance: Excellent
Recommended cleaning products:	(Hot) water, soap, most industrial cleaners, alcohol, light fuel, turpentine, white spirit

WoodBond-S