## Hardsqueeze



| Cover Type:                    | Hard rubber (ebonite)   |   |
|--------------------------------|---|---|
| Possible applications:         | Textile wet finishing & sizing: foulard squeez roller   | ze roll, sink and deflector roll, outle           |
|                                | Diverse applications in a lot of industrial are excellent chemical stability and high hardne        |   |
| Hardness Range:                | 85 Shore D  |   |
| Recommended Cover Thickness:   | min. 2 mm - max. 20 mm  |   |
| Temperature resistance:        |   | ntinuous 90°C / peak 95°C                         |
|                                | Wet: cor  | ntinuous 90°C / peak 95°C                         |
| Properties and advantages:     | Stable, hardwearing material  |   |
|                                | High chemical stability in hot water, acid and alkaline environment up to 95°C                      |   |
| Chemical resistance:           | Acid solutions:   | Very good   |
|                                | Alkaline solutions:   | Good  |
|                                | Hot water and steam:  | Very good   |
|                                | Ozone:  | Moderate  |
|                                | Oil and grease:   | Not suited  |
|                                | On and grease.  |   |
|                                | Aromatic solvents (toluene, benzene,):  | Not suited  |
|                                | Aromatic solvents (toluene, benzene,): Chlorinated solvents:  | Not suited<br>Not suited                          |
|                                | Aromatic solvents (toluene, benzene,): Chlorinated solvents: Polar solvents (MEC, ether, acetate,): | Not suited<br>Not suited<br>Moderate              |
|                                | Aromatic solvents (toluene, benzene,): Chlorinated solvents:  | Not suited<br>Not suited                          |
| Recommended cleaning products: | Aromatic solvents (toluene, benzene,): Chlorinated solvents: Polar solvents (MEC, ether, acetate,): | Not suited<br>Not suited<br>Moderate<br>Very good |



Print date: 27/04/2024