EasyLac



Cover Type:	Polyurethane		
Possible applications:	Applicator rollers for "roll coating" systems in all industrial areas		
	"Mailander" applicator rollers for metal packaging sheet coating		
Hardness Range:	55, 62, 65 Shore A		
Recommended Cover Thickness:	min. 15 mm - max. 25 mm		
Temperature resistance:		ontinuous 70°C / peak 80°C ontinuous 30°C / peak 40°C	
Properties and advantages:	Good solvent resistance, suited for solvent-based coating applications		
	Very high purity and homogenity		
	High surface energy, good transfer behaviour		
Chemical resistance:	Acid solutions: Alkaline solutions: Hot water and steam: Ozone: Oil and grease: Aromatic solvents (toluene, benzene,): Chlorinated solvents: Polar solvents (MEC, ether, acetate,): Alcohols (ethanol, IPA,):	Not suited Not suited Not suited Moderate Very good Good Moderate Moderate Moderate	
Recommended cleaning products:	Water, soap & detergents, fuel, Solvesso, turpentine – with moderation: alcohol based cleaners, MEC		

