

# NeoFlex SBD



<b>Cover Type:</b>	Special polyurethane														
<b>Possible applications:</b>	Suction Blind Drilled Press Roll														
<b>Hardness Range:</b>	5, 10, 15, 20, 25, 30, 35 PJ														
<b>Available Colours:</b>	lilac														
<b>Recommended Cover Thickness:</b>	max. 25 mm														
<b>Temperature resistance:</b>	Dry: continuous 80°C / peak 110°C														
<b>Properties and advantages:</b>	<ul style="list-style-type: none"><li>-Optimal dewatering due to very strong mechanical properties leading to highest operative void volume under pressure in the nip</li><li>Longest dewatering stability due to highest Nip &amp; Peak Pressure stability</li><li>Long lifetime due to excellent abrasion resistance without hydrolysis</li><li>Shortest drainage time due to tailor made surface design (Surface Manager)</li><li>Very limited energy losses (driving and pressing) due to very low heat buildup</li><li>Longest nip pressing stability in operation due to the fact that the cover has no hardening &amp; no ageing</li><li>Excellent runnability due to high vibration absorption behaviour</li><li>Less risk of open area contamination due to surface self cleaning properties</li><li>Long resistance vs stress due to high performance bonding system</li></ul>														
<b>Doctoring:</b>	HDPE blade at 1 to 2 mm from surface or 18 deg & 50 to 70 N/m if loaded, HDPE foil blade 10 deg, 50 to 70 N/m Dry doctoring is prohibited														
<b>Internal cooling:</b>	if needed : recommended inlet T° of the inner cooling water : 30 to 45 °C, water flow to be adjusted in order to respect 5°C < Delta T (out-in) < 10°C														
<b>Possible surface design:</b>	S (Suction), BD (Blind Drilled), G (Grooved) & combined SBD, SG, SBDG, BDG														
<b>Chemical resistance:</b>	<table><tr><td>Acid solutions:</td><td>Moderate</td></tr><tr><td>Alkaline solutions:</td><td>Moderate</td></tr><tr><td>Hot water and steam:</td><td>Very good</td></tr><tr><td>Ozone:</td><td>Very good</td></tr><tr><td>Oil and grease:</td><td>Good</td></tr><tr><td>Chlorinated solvents:</td><td>Not suited</td></tr><tr><td>Polar solvents (MEC, ether, acetate,...):</td><td>Not suited</td></tr></table>	Acid solutions:	Moderate	Alkaline solutions:	Moderate	Hot water and steam:	Very good	Ozone:	Very good	Oil and grease:	Good	Chlorinated solvents:	Not suited	Polar solvents (MEC, ether, acetate,...):	Not suited
Acid solutions:	Moderate														
Alkaline solutions:	Moderate														
Hot water and steam:	Very good														
Ozone:	Very good														
Oil and grease:	Good														
Chlorinated solvents:	Not suited														
Polar solvents (MEC, ether, acetate,...):	Not suited														
<b>Recommended cleaning products:</b>	- Good resistance to standard chemicals normally used in paper machines														
<b>Remark:</b>	- Reference list available on demand														