



Type de revêtement:	Carbure	
Applications possibles:	Winder Drum Roll Winder Rider Roll	
Gamme de dureté:	1100 Vickers	
Epaisseur conseillée:	Standard 125 µm	max. 1000 µm
Résistance à la température:	Sec:	continu 500°C / en pointe 500°C
Propriétés et avantages:	<ul style="list-style-type: none">- Optimized driving of the paper due to adapted surface roughness (standard, R and R Plus versions available)- Paper grip stability due to roughness stability in operation- Long lifetime due to high abrasion resistance- No wrinkle or other damage to the paper- Can be produced On Site and In Workshop	
Caractéristiques:	Force d'adhérence: Rugosité de surface (Ra):	> 75 MPa min. 4 µm - max. 12 µm
Résistance chimique:	Solutions acides: Solutions alcalines: Eau chaude et vapeur: Ozone: Huiles et matières grasses: Solvants chlorés: Solvants polaires (MEC, éther, acétat,...):	Pas bon Moyen Pas bon Pas bon Excellent Bon Excellent
Produits de nettoyage conseillés:	- Bonne résistance aux produits standards généralement utilisés sur machine à papier	
Remarque:	- liste de référence disponible sur demande	