

WoodCoat-SP



Cover Type:	Rubber	
Possible applications:	<p>Production of wood, wood board and wood laminate :</p> <ul style="list-style-type: none">- varnishing and lacquering rollers for water or oil based coatings- oiling and staining rollers- impregnation rollers- catalyst and primer application <p>Possibility to foresee microgrooves up to 80 grooves/inch</p>	
Hardness Range:	40, 45, 50, 55, 60, 65, 70, 80 Shore A	
Available Colours:	black	
Recommended Cover Thickness:	min. 12 mm - max. 25 mm	
Temperature resistance:	Dry:	continuous 100°C / peak 110°C
	Wet:	continuous 60°C / peak 70°C
Properties and advantages:	<p>Very good surface wetting and transfer properties</p> <p>Good physical properties and lifetime</p> <p>High purity and homogeneity</p> <p>Excellent oil resistance</p> <p>Easy to grind and to groove</p>	
Chemical resistance:	Acid solutions:	Moderate
	Alkaline solutions:	Good
	Hot water and steam:	Good
	Ozone:	Very good
	Oil and grease:	Exceptional
	Aromatic solvents (toluene, benzene,...):	Moderate
	Chlorinated solvents:	Not suited
	Polar solvents (MEC, ether, acetate,...):	Not suited
	Alcohols (ethanol, IPA,...):	Very good
	Ageing resistance:	Excellent
Recommended cleaning products:	(Hot) water, soap, most industrial cleaners, alcohol, light fuel, turpentine, white spirit	