

WoodCoat-SP



Cover Type:	Rubber
Possible applications:	Production of wood, wood board and wood laminate : - varnishing and lacquering rollers for water or oil based coatings - oiling and staining rollers - impregnation rollers - catalyst and primer application Possibility to foresee microgrooves up to 80 grooves/inch
Hardness Range:	40, 45, 50, 55, 60, 65, 70, 80 Shore A
Available Colours:	black
Recommended Cover Thickness:	min. 12 mm - max. 25 mm
Temperature resistance:	Dry: continuous 100°C / peak 110°C Wet: continuous 60°C / peak 70°C
Properties and advantages:	Very good surface wetting and transfer properties Good physical properties and lifetime High purity and homogeneity Excellent oil resistance Easy to grind and to groove
Chemical resistance:	Acid solutions: Moderate Alkaline solutions: Good Hot water and steam: Good Ozone: Very good Oil and grease: Exceptional Aromatic solvents (toluene, benzene,...): Moderate Chlorinated solvents: Not suited Polar solvents (MEC, ether, acetate,...): Not suited Alcohols (ethanol, IPA,...): Very good Ageing resistance: Excellent
Recommended cleaning products:	(Hot) water, soap, most industrial cleaners, alcohol, light fuel, terpentine, white spirit