

WoodBond-XP



Cover Type:	Rubber	
Possible applications:	Production of wood, wood board and wood laminate : - applicator and transfer rollers for cold glue, water or formaldehyde based - applicator rollers for hardeners and catalysts	
Hardness Range:	60, 65, 70, 80 Shore A	
Recommended Cover Thickness:	min. 10 mm - max. 20 mm	
Temperature resistance:	Dry: Wet:	continuous 120°C / peak 130°C continuous 80°C / peak 90°C
Properties and advantages:	Good surface wetting and transfer properties Excellent physical properties and lifetime High purity and homogeneity Easy to grind and to groove	
Chemical resistance:	Acid solutions: Alkaline solutions: Hot water and steam: Ozone: Oil and grease: Aromatic solvents (toluene, benzene,...): Chlorinated solvents: Polar solvents (MEC, ether, acetate,...): Alcohols (ethanol, IPA,...): Ageing resistance:	Excellent Excellent Excellent Excellent Moderate Moderate Moderate Moderate Very good Excellent
Recommended cleaning products:	(Hot) water, acid and alkaline cleaners, soap and detergents, alcohol based cleaners	