## **Press Plast Gold**



Cover Type:	Special rubber	
Possible applications:	Tissue paper converting : marrying laminator roller - recommended in case of multi-plies embossing	
Hardness Range:	72 Shore D	
Recommended Cover Thickness:	min. 10 mm - max. 15 mm	
Temperature resistance:	Dry: continuous 110°C / peak 125°C	
Properties and advantages:	Guarantees perfect assembly of the plies even if they are numerous, preserving product softness, thanks to the narrow nip and increased specific pressure No back-side effect (re-embossing of the inner ply) Excellent resistance to mechanical stress	
	Very good abrasion resistance and lifetime	
	Increased release properties	
Chemical resistance:	Acid solutions: Alkaline solutions: Hot water and steam: Ozone: Oil and grease: Aromatic solvents (toluene, benzene,): Chlorinated solvents: Polar solvents (MEC, ether, acetate,): Alcohols (ethanol, IPA,): Ageing resistance:	Very good Good Very good Good Not suited Not suited Not suited Very good Very good
Recommended cleaning products:	(Warm) water, soap, industrial cleaners and detergents, alcohol, (diluted) acid cleaners	

